

Anisotropic superconducting gap in transuranium superconductor PuRhGa₅: Ga NQR study on a single crystal

Hironori SAKAI^{1*}, Yo TOKUNAGA¹, Tatsuya FUJIMOTO¹, Shinsaku KAMBE¹, Russell E. WALSTEDT¹, Hiroshi YASUOKA¹, Dai AOKI², Yoshiya HOMMA², Etsuji YAMAMOTO¹, Akio NAKAMURA¹, Yoshinobu SHIOKAWA^{1,2}, Kunihisa NAKAJIMA³, Yasuo ARAI³, Tatsuma D. MATSUDA¹, Yoshinori HAGA¹, Yoshichika ŌNUKI^{1,4}

¹*Advanced Science Research Center, Japan Atomic Energy Research Institute, Tokai, Ibaraki 319-1195, JAPAN*

²*Institute for Materials Research, Tohoku University, Oarai, Ibaraki 311-1313, JAPAN*

³*Department of Nuclear Energy System, Japan Atomic Energy Research Institute, Tokai, Ibaraki 319-1195, JAPAN*


⁴*Graduate School of Science, Osaka University, Toyonaka, Osaka 560-0043, JAPAN*

^{69,71}Ga NMR/NQR studies have been performed on a single crystal of the transuranium superconductor PuRhGa₅ with $T_c \simeq 9$ K. We have observed a ⁶⁹Ga NQR line at ~ 29.15 MHz, and assigned it to the 4i Ga site using the NMR results. The ⁶⁹Ga NQR spin-lattice relaxation rate $1/T_1$ shows no coherence peak just below T_c , but obeys a T^3 behavior below T_c . This result strongly suggests that PuRhGa₅ is an unconventional superconductor having an anisotropic superconducting gap. The gap amplitude $2\Delta_0(T \rightarrow 0) \simeq 5k_B T_c$ and the residual density of states $N_{\text{res}}(T=0)/N_0(T=T_c) \simeq 0.25$ have been determined assuming a simple polar function of the form $\Delta(\theta, \phi) = \Delta_0 \cos \theta$, where θ and ϕ are angular parameters on the Fermi surface.

KEYWORDS: PuRhGa₅, Superconductivity, Ga NQR

The recent discovery of Pu-based superconductors PuTGa₅ (T=Co, Rh) has stimulated interest in further experiments on transuranium compounds. A lot of attention is now focused on these Pu heavy-fermion compounds, which have relatively high superconducting (SC) transition temperatures, *i.e.*, $T_c \simeq 18$ K¹ (PuCoGa₅) and $T_c \simeq 9$ K² (PuRhGa₅). The PuTGa₅ systems belong to a large family of “115 compounds”, which all crystallize in the same quasi-two-dimensional structure. In this family, the Ce115 isomorphs CeTIn₅ (T'=Co, Ir, Rh),³⁻⁵ which are well-known 4f heavy fermion systems with antiferromagnetic tendencies, show *d*-wave superconductivity with relatively low T_c values: $T_c = 0.4$ K and 2.3 K for CeIrIn₅ and CeCoIn₅, respectively.⁶⁻⁹ On the other hand, the U115¹⁰⁻¹² and Np115¹³⁻¹⁶ compounds usually show itinerant magnetic order or Pauli paramagnetism, but up to now have not shown any superconductivity. Band calculations^{17, 18} and de Haas-van Alphen experiments^{10, 14, 15, 19, 20} have

*E-mail address: piros@popsvr.tokai.jaeri.go.jp

Fig. 1. Crystal structure of PuRhGa₅.

revealed that An115 (An=U, Np, Pu, ...) compounds often have cylindrical Fermi surfaces, reflecting a quasi-two-dimensional character.

To elucidate the relatively high T_c values exhibited by PuTGa₅, it is important to determine the pairing symmetry, which reflects the SC pairing mechanism. Nuclear Magnetic Resonance (NMR and NQR) is a microscopic probe well-suited to this task. In particular, the T dependence of NQR (zero-field) spin-lattice relaxation rates ($1/T_1$) can provide crucial information regarding the SC pairing symmetry. In this letter, we report ^{69,71}Ga NMR/NQR experimental results above and below the SC transition in PuRhGa₅.

A single crystal of PuRhGa₅ has been prepared using the Ga flux method.²¹ The dimensions of the single crystal are $1 \times 2 \times 3$ mm³. This crystal has been attached with varnish to a silver cap for thermal contact, coated with epoxy resin, and sealed tightly in a polyimide tube in order to avoid radiation contamination. The sealed sample was then mounted into an rf coil. NQR/NMR measurements have been carried out in the temperature range 1.5-300 K using a phase-coherent, pulsed spectrometer, which has been installed in the radiation controlled area. T_1 was measured for the Ga NQR lines using the saturation-recovery method. The recovery of nuclear magnetization $M(t)$ from a saturation pulse comb was single-exponential type, $\{M(t) - M(\infty)\}/M(\infty) \propto \exp(-3t/T_1)$, in the whole temperature range. The superconductivity of PuRhGa₅ has been reported to be influenced by self-radiation damage due to spontaneous α decay, *i.e.*, T_c decreases gradually with $dT_c/dt \simeq -0.2 \sim -0.5$ K/month.² Accordingly, in order to study the superconductivity of PuRhGa₅, brief and timely experimental measurements are required. In our experiments, the bulk T_c was determined by both *in situ* ac susceptibility (χ_{ac}) measurements using the rf coil, and the sudden decrease of the NQR signal intensity, as mentioned below. T_c was found to be 8.5 K in zero field at the starting point of the present experiments, which was one month after the synthesis of the single crystal. All the NMR/NQR experiments reported here were conducted within a single month.

PuRhGa₅ crystallizes in the tetragonal HoCoGa₅ structure with lattice parameters of $a =$




Fig. 2. (a) Field-swept NMR spectrum in PuRhGa_5 at 10 K at a frequency of 84.1 MHz with the applied field (H_0) parallel to the c axis. Spectral assignments are denoted by arrows, and the zero-shift positions $^{69,71}K = 0$ are also indicated. The two NMR lines near $^{69,71}K = 0$ originate from residual Ga flux. (b) Enlarged spectra around 90 kOe at a same frequency of 84.1 MHz at different angles (θ) between H_0 and the c axis.

4.2354 and $c = 6.7939 \text{ \AA}$,² as shown in Fig. 1. This structure can be viewed as alternating PuGa_3 and RhGa_2 layers stacked along the c axis. There are two crystallographically inequivalent Ga sites, which are denoted Ga(1) (the $1c$ site) and Ga(2) (the $4i$ site), respectively. The Ga(1) site is surrounded by four Pu atoms in the c plane. On the other hand, the Ga(2) site is surrounded by two Pu and two Rh atoms in the a plane. Therefore, in an applied field (H_0), the Ga(2) sites split into two magnetically inequivalent sites, except for the case of $H_0 \parallel c$ axis.

Figure 2(a) shows a field-swept NMR spectrum in the normal state at $T = 10 \text{ K}$ and a frequency of 84.1 MHz, with H_0 parallel to the c -axis. This spectrum is well explained if we associate two sets of lines to $^{69}\text{Ga}(2)$ and $^{71}\text{Ga}(2)$ sites, where each set has a center line and two quadrupolar satellite lines denoted by arrows in Fig. 2. Since the Ga(2) sites have a lower local symmetry than the Ga(1), with four-fold axial symmetry, each center line lies at an asymmetric position between the satellites. This is due to the second-order quadrupolar effect. The Knight shift (K), electric field gradient parameter ($\nu_{\text{EFG}} \equiv e^2qQ/2h$), and asymmetry parameter (η) of the Ga(2) site have been estimated from second-order perturbation theory, where eQ is nuclear quadrupole moment and eq is the largest electric field gradient.²² The calculated K , ν_{EFG} and η at 10 K are $K \simeq 0.19 \%$, $^{69}\nu_{\text{EFG}} = 28.2 \text{ MHz}$, $^{71}\nu_{\text{EFG}} = 17.4 \text{ MHz}$, and $\eta \simeq 0.42$, respectively. Here, the ratio $^{69}\nu_{\text{EFG}}/^{71}\nu_{\text{EFG}} \simeq 1.6$ is consistent with that of the nuclear quadrupole moments ($^{69}Q/^{71}Q = 1.59$). These values of ν_{EFG} and η for Ga(2) sites are similar to those of the U115 ²³ and Np115 ^{24,25} families, *e.g.*, $^{69}\nu_{\text{EFG}}$ and η at the same site are 27.5 MHz and 0.2 for UPtGa_5 , and $\sim 27.3 \text{ MHz}$ and ~ 0.29 for NpCoGa_5 , respectively.

It should be noted here that the above assignment of Ga(2) NMR lines has been confirmed further by the field orientation dependence (θ) of the spectra in Fig. 2(b), where θ is an angle




Fig. 3. $^{69}\text{Ga}(2)$ NQR spectrum with rf field parallel to c axis at zero field in PuRhGa_2 . The inset shows the temperature dependence of the $^{69}\text{Ga}(2)$ NQR frequency.

between H_0 and the c axis. As seen in Fig.2(b), a small increase of θ causes a splitting of each NMR line. If these lines were ascribed to $\text{Ga}(1)$ sites, such a splitting could not be expected, because the $\text{Ga}(1)$ sites remain equivalent under any applied field. The $^{69,71}\text{Ga}(1)$ NMR signals are very weak due to a short T_2 , and not seen in Fig.2(a) under this experimental condition.

Next, we turn to the zero-field NQR experiments. The $^{69}\text{Ga}(2)$ NQR spectrum of the single crystal has been observed at $\nu_Q \simeq 29.15$ MHz as shown in Fig.3. Here, the value of ν_Q is consistent with the expected frequency, $\nu_Q = \nu_{\text{EFG}} \sqrt{1 + \eta^2/3}$, extracted from ν_{EFG} and η in the NMR results. The narrow NQR line width (~ 20 kHz) assures us that this sample is still of good quality, *i.e.*, broadening effects due to defects and/or impurities are not serious at this point. The temperature dependence of ν_Q is shown in the inset of Fig.3. The value of ν_Q increases gradually as temperature decreases from 300 K, and saturates below ~ 50 K. The slight temperature dependence of ν_Q is caused by that of ν_{EFG} , because the value of η is found to be temperature-independent from NMR results. Note that the $^{71}\text{Ga}(2)$ NQR line has been observed concurrently at the frequency of 18.38 MHz at $T = 10$ K.

T_1 has been measured for both $^{69}\text{Ga}(2)$ and $^{71}\text{Ga}(2)$ NQR lines in order to clarify the T_1 process. The ratio $^{69}T^{-1}/^{71}T^{-1}$ of data so obtained is found to be nearly equal to $^{69}\gamma_n^2/^{71}\gamma_n^2$ below ~ 150 K, where γ_n denotes the nuclear gyromagnetic ratio. This indicates that the magnetic dipole relaxation mechanism is dominant over quadrupolar relaxation, at least in the low temperature range. The inset to Fig.4 shows the result of *in situ* χ_{ac} measurements. Here, this measurement was performed before and after NQR T_1 measurements. The onset T_c was determined to be 8.5 K from χ_{ac} data, where the distribution of T_c was estimated to be less than ~ 0.5 K. In the duration of a single week to obtain NQR T_1 data, the onset T_c was unchanged within less than ~ 0.1 K. It is noted that the NQR signal intensity was weakened suddenly below 8.5 K, because the rf pulse was attenuated due to the Meissner effect.

Figure 4 shows the temperature dependence of $1/T_1$ obtained for the $^{69}\text{Ga}(2)$ NQR line. In




Fig. 4. Temperature dependence of $1/T_1$ for the $^{69}\text{Ga}(2)$ NQR line in PuRhGa_5 . The inset shows the temperature dependence of *in situ* ac susceptibility using the rf coil. The solid curve has been calculated assuming a line-node gap with $2\Delta_0(0) \sim 5k_B T_c$ and a residual DOS $N_{\text{res}}/N_0 \sim 0.25$. The broken curve shows the same calculation without any residual DOS. The dotted line shows Korringa-like behavior for comparison.

the normal state from T_c to ~ 30 K, $1/T_1$ is approximately proportional to T , *i.e.*, Korringa-like behavior associated with typical coherent Fermi liquid state. The values of $1/T_1$ above ~ 30 K fall below Korringa-like behavior, which is thought to be related to a reduction in the coherence of the Fermi liquid state. This Korringa-like behavior is also confirmed by preliminary high-field NMR T_1 measurements at $H_0 \sim 110$ kOe ($\parallel c$), where T_c is suppressed down to ~ 4 K. The present T_1 results suggest that the SC state in PuRhGa_5 sets in after a Fermi liquid state is established below ~ 30 K. Further discussion of T_1 in the normal state will be presented elsewhere.

In the SC state, we have found that $1/T_1$ shows no coherence peak just below T_c , but decreases $\propto T^3$ as T decreases, as seen in Fig.4. Besides, a deviation from T^3 behavior is also observed for T well below T_c . The $1/T_1$ behavior we found cannot be explained in terms of a fully open SC gap with *s*-wave symmetry. These results strongly suggest that PuRhGa_5 has an anisotropic gap in the SC state. We can reproduce the behavior of $1/T_1$ under the assumption of *d*-wave symmetry with line nodes, which is widely accepted to be realized in the Ce115 family. This calculation has been done in the following way: An anisotropic gap function is assumed as a polar function $\Delta(\theta, \phi) = \Delta_0 \cos \theta$, where θ and ϕ mean angular parameters on

the Fermi surface, and the temperature dependence of Δ_0 is assumed to be BCS-like. Then, the temperature dependence of $1/T_1$ below T_c has been calculated from the following integral,

$$\left(\frac{1}{T_1}\right)/\left(\frac{1}{T_1}\right)_{T=T_c} = \frac{2}{k_B T} \int \left\langle \frac{N_s(E)^2}{N_0^2} \right\rangle_{\theta, \phi} f(E)[1 - f(E)] dE,$$

where $N_s(E) = N_0 E / \sqrt{E^2 - \Delta(\theta, \phi)^2}$ with N_0 being the density of states (DOS) in the normal state, $f(E)$ is the Fermi distribution function, and $\langle \cdots \rangle_{\theta, \phi}$ means the angular average over the Fermi surface. From the best fit of the experimental data to this calculation, we evaluate the SC gap $2\Delta_0(T \rightarrow 0) \simeq 5k_B T_c$ with a residual DOS ($N_{\text{res}}/N_0 \simeq 0.25$) in the SC state. This gap estimate is similar to that of CeIrIn₅ with $T_c \simeq 0.4$ K,⁷ while it is smaller than that of CeCoIn₅, *i.e.*, $2\Delta_0(0) \simeq 8k_B T_c$ with $T_c \simeq 2.3$ K.⁶ In the high- T_c cuprates, the value of $2\Delta_0(0)$ often reaches $\sim 10k_B T_c$. PuRhGa₅ would be classified as an intermediate-coupling superconductor.

The finite residual DOS in the *d*-wave SC state is mostly caused by potential scattering associated with nonmagnetic impurities, distortion, and contamination with a secondary phase etc.^{26,27} In Pu compounds, the influence of unavoidable potential scattering coming from self-radiation damage is also expected. In the literature, the relation between the size of the residual DOS and the reduction rate of T_c has been calculated based on an anisotropic SC model, where the scattering is treated in the unitarity (strong) limit.^{28,29} Using the relation with $N_{\text{res}}/N_0 \simeq 0.25$ observed in our sample, we can obtain $T_c/T_{c0} \simeq 0.94$, where T_{c0} is the intrinsic value of T_c without potential scattering effects. We can estimate the maximum (intrinsic) $T_{c0} = 9.0$ K using the $T_c = 8.5$ K in our sample observed a month after synthesis. This T_{c0} is consistent with the observed T_c just after synthesis. The aging effect on the residual DOS in the SC gap will be an interesting effect to study in Pu-based superconductors.

In summary, we have succeeded in ^{69,71}Ga NMR/NQR measurements for the Ga(2) site of transuranium superconductor PuRhGa₅. The ^{69,71}Ga(2) NQR lines have been found at frequencies consistent with an analysis based on NMR results. The NQR $1/T_1$ in the SC state shows no coherence peak just below T_c , but obeys a T^3 behavior below T_c . Such a result is strong evidence that PuRhGa₅ is an unconventional superconductor with an anisotropic SC gap. Assuming a *d*-wave symmetry, the SC gap $\Delta_0(0) \simeq 5k_B T_c$ with $N_{\text{res}}/N_0 \simeq 0.25$ has been evaluated. To determine the parity of SC pairing in PuRhGa₅, Knight shift measurements are in progress.

We thank Dr. T. Hotta and Dr. T. Maehira for helpful discussions. This work was supported in part by the Grant-in-Aid for Scientific Research of MEXT (Grants. No. 14340113).

-Added note. After completion of this paper, an NMR/NQR study on the closely related compound PuCoGa₅ by Curro *et al.*, has appeared.³⁰ It is useful to note some contrasting points in the behavior of these two Pu superconductors. First, the T_1 results of Curro *et al.*, are also analyzed in terms of *d*-wave superconductivity, finding a SC gap value $2\Delta_0 \simeq 8k_B T_c$ (*c.f.*,

$5k_{\text{B}}T_{\text{c}}$ for PuRhGa_5). Secondly, the T -variation of $(T_1T)^{-1}$ for PuCoGa_5 shows a monotonic increase right down to T_{c} , whereas the Rh isomorph shows a Korringa-like behavior below ~ 30 K.

References

- 1) J. L. Sarrao, L. A. Morales, J. D. Thompson, B. L. Scott, G. R. Stewart, F. Wastin, J. Rebizant, P. Boulet, E. Colineau, and G. H. Lander: *Nature* **420** (2002) 297.
- 2) F. Wastin, P. Boulet, J. Rebizant, E. Colineau, and G. H. Lander: *J. Phys.: Condens. Matter* **15**, S2279 (2003).
- 3) H. Hegger, C. Petrovic, E. G. Moshopoulou, M. F. Hundley, J. L. Sarrao, Z. Fisk, and J. D. Thompson: *Phys. Rev. Lett.* **84** (2000) 4986.
- 4) C. Petrovic, R. Movshovich, M. Jaime, P. G. Pagliuso, M. F. Hundley, J. L. Sarro, Z. Fisk, and J. D. Thompson: *Europhys. Lett.* **53** (2001) 354.
- 5) C. Petrovic, P. G. Pagliuso, M. F. Hundley, R. Movshovich, J. L. Sarrao, J. D. Thompson, Z. Fisk, and P. Monthoux: *J. Phys.: Condens. Matter* **13** (2001) L337.
- 6) Y. Kohori, Y. Yamato, Y. Iwamoto, T. Kohara, E. D. Bauer, M. B. Maple, and J. L. Sarrao: *Phys. Rev. B* **64** (2001) 134526.
- 7) G.-q. Zheng, K. Tanabe, T. Mito, S. Kawasaki, Y. Kitaoka, D. Aoki, Y. Haga, and Y. Ōnuki: *Phys. Rev. Lett* **86** (2001) 4664.
- 8) T. Mito, S. Kawasaki, G.-q. Zheng, Y. Kawasaki, K. Ishida, Y. Kitaoka, D. Aoki, Y. Haga, and Y. Ōnuki: *Phys. Rev. B* **63** (2001) 220507R.
- 9) N. J. Curro, J. L. Sarrao, J. D. Thompson, P. G. Pagliuso, Š. Kos, Ar. Abanov, and D. Pines: *Phys. Rev. Lett.* **90** (2003) 227202.
- 10) Y. Tokiwa, T. Maehira, S. Ikeda, Y. Haga, E. Yamamoto, A. Nakamura, Y. Ōnuki, M. Higuchi, and A. Hasegawa: *J. Phys. Soc. Jpn.* **70** (2001) 2982.
- 11) S. Ikeda, Y. Tokiwa, T. Okubo, Y. Haga, E. Yamamoto, Y. Inada, R. Settai, and Ōnuki: *J. Nucl. Sci. Technol. (suppl.)* **3** (2002) 206.
- 12) Y. Tokiwa, Y. Haga, N. Metoki, Y. Ishii, and Ōnuki: *J. Phys. Soc. Jpn.* **71** (2002) 725.
- 13) E. Colineau, P. Javorský, P. Boulet, F. Wastin, J. C. Griveau, J. Rebizant, J. P. Sanchez, and G. R. Stewart: *Phys. Rev. B* **69** (2004) 184411.
- 14) D. Aoki, E. Yamamoto, Y. Homma, Y. Shiokawa, A. Nakamura, Y. Haga, R. Settai, and Y. Ōnuki: *J. Phys. Soc. Jpn.* **73** (2004) 519.
- 15) D. Aoki, E. Yamamoto, Y. Homma, Y. Shiokawa, A. Nakamura, Y. Haga, R. Settai, T. Takeuchi, and Y. Ōnuki: *J. Phys. Soc. Jpn.* **73** (2004) 1665.
- 16) D. Aoki, E. Yamamoto, Y. Homma, Y. Shiokawa, A. Nakamura, Y. Haga, R. Settai, and Y. Ōnuki: *J. Phys. Soc. Jpn.* **73** (2004) 2608.
- 17) T. Maehira, T. Hotta, K. Ueda, and A. Hasegawa: *Phys. Rev. Lett.* **90** (2003) 207007.
- 18) T. Maehira, M. Higuchi and A. hasegawa: *Physica B* **329-333** (2003) 574.
- 19) Y. Tokiwa, S. Ikeda, Y. Haga, T. Okubo, T. Iizuka, K. Sugiyama, A. Nakamura and Y. Ōnuki: *J. Phys. Soc. Jpn.* **71** (2002) 845.
- 20) S. Ikeda, Y. Tokiwa, Y. Haga, E. Yamamoto, T. Ōkubo, M. Yamada, N. Nakamura, K. Sugiyama, K. Kindo, Y. Inada, H. Yamagami and Y. Ōnuki: *J. Phys. Soc. Jpn.* **72** (2003) 576.
- 21) Y. Haga *et al.*: submitted to *J. Phys. Soc. Jpn.*
- 22) A. Abragam: *The Principles of Nuclear Magnetism* (Oxford University Press, London, 1961).
- 23) H. Kato, H. Sakai, Y. Tokunaga, Y. Tokiwa, S. Ikeda, Y. Ōnuki, S. Kambe, and R. E. Walstedt: *J. Phys Soc. Jpn.* **72** (2003) 2357.

- 24) S. Kambe *et al.*, to be published in *Physica B*.
- 25) H. Sakai *et al.*: preparation.
- 26) K.Ishida Y.Kitaoka, N.Ogata, T.Kamino, K.Asayama, J.R.Cooper and N.Athanassopoulou:
J.Phys. Soc. Jpn **62**, (1993) 2803.
- 27) Y.Kitaoka, K.Ishida and K.Asayama: *J.Phys. Soc. Jpn* **63**, (1994) 2052.
- 28) T. Hotta: *J. Phys. Soc. Jpn.* **62** (1993) 274.
- 29) K.Miyake, unpublished.
- 30) N. J. Curro, T. Caldwell, E. D. Bauer, L. A. Morales, M. J. Graf, Y. Bang, A. V. Balatsky, J. D. Thompson, and J. L. Sarrao: *Nature* **434**, 622 (2005).